


VOSSEN



Carpet Tiles

FOREST

Product	FOREST
Construction	LOOP
Pile Fiber Composition	%100 PP Olefin
Yarn Type	BCF
Dye Method	Solution Dyed
Pile Weight	475g/m ²
Number of Tufts	250000/m ²
Tufting Gauge	10/1"
Primary Backing	Non-Woven
Secondary Backing	Environmental Bitumen
Tile Size	50 cm x 50 cm
Total Tile Height	5.5-6.0 mm
Pile Treatment	INVISTA Anti-Soil Treatment

Performance Specifications

Wear Classification	Heavy Contract	
VOC Emission	ASTM D06-5116	<0.5 mg/m ² /hour (CRI GLP)
Flammability	ASTM D2859-//FF 16//70-1CFR 1630	Pass 8/8
Critical Radiant Flux	EN ISO 2002 - 1 - 9239	Dfl - s1
Static Propensity	ISO 6356	0.2 kV
Color Fastness	AATCC/16	5/5 on Grey Scale
Thermal Resistance	ISO 8302	.04m ² K/W
Impact Sound Insulation	ISO 8-140	ΔLw 23dB
Sound Absorption Level	EN ISO 11654	αw: 0.15(H)
Soiling Propensity	ASTM D 00-6540	4
Dimensional Stability	EN 986	< %0.20
Castor Chair Test	DIN 54324	R ≥ 2.4
Smoke Density	EN ISO 1:2002-9239	<450

The above Information is subject to modification for the benefit of further improvement.

